

GOUDSMIT

MAGNETICS

T: +31 40 221 32 83

E: info@goudsmitmagnets.com

Website: www.goudsmitmagnets.com

Goudsmit grade code	Remanence B_r	Normal coercivity H_{cB}	Intrinsic coercivity H_{cJ}	Maximum energy product $(BH)_{max}$	Remanence temperature coefficient $\alpha(B_r)$	Intrinsic coercivity temperature coefficient $\beta(H_{cJ})$	Maximum operating temperature T_{max}
	minimum value	minimum value	minimum value	minimum value	minimum typical value	minimum typical value	maximum value
	[mT]	[kA/m]	[kA/m]	[kJ/m ³]	[%/°C]	[%/°C]	[°C]
N28VH	1020	780	3104	207	-0.10	-0.393	250
N30VH	1080	812	3104	223	-0.10	-0.393	250
N33VH	1130	812	3104	247	-0.10	-0.393	250
N35VH	1170	883	3104	263	-0.10	-0.393	250
N38VH	1220	923	3104	287	-0.10	-0.393	250